



Nu-Klad 807B

Self Leveling Epoxy

Product Data/ Application Instructions

- **Tough and abrasion resistant floor topping**
- **Excellent wear and chemical resistance**
- **Smooth and easy cleanable**
- **Contains no solvents**

Typical Uses

Nu-Klad 807B is used for the protection of concrete floors in the food and beverage industry, industrial and commercial warehouses, (nuclear) power plants and other locations where a heavy duty, smooth and cleanable floor topping is required.

Resistance

Nu-Klad 807B is a solvent free epoxy based self levelling floor topping. It has excellent wear resistance and provides a smooth finish. Nu-Klad 807B is easily cleaned from dirt and grease, resisting normal cleaning procedures. Nu-Klad 807B resists splash and spillage of a wide range of industrial chemicals and cleaning agents. For specific recommendations, ask your PPG representative.

Physical Data

Finish	smooth and glossy
Colour	RAL 1014, RAL 3009, Ral 5009, RAL 6028, RAL 7004, RAL 7012
Components	2
Mixing ratio (by weight)	
resin	6.4 parts
cure	1 part
Curing mechanism	chemical reaction between components
Dry film thickness	1½ mm - 3 mm
Volume solids	100%
Specific gravity	1.67 kg/l (mixed product)
Calculated coverage	0.3m ² /kg at 2 mm
Allow for application losses, surface irregularities, etc.	
Flash points	
(Closed Cup)	°C °F
resin	60 140
cure	60 140
Thinner 90-58	24 75

TYPICAL PROPERTIES

Compressive strength	>70 N/mm ²
Flexural strength	>50 N/mm ²
Tensile strength	>15 N/mm ²
Modulus of Elasticity	<3000 N/mm ²

Nu-Klad 807B

Surface Preparation

Concrete with a trowelled surface is preferred and will give the best overall appearance. Concrete floors should be brought up to grade.

Light abrasive blasting or grinding is recommended to remove all previous coatings, chalk and surface glaze or laitance.

Mixing

Use a power mixer such as ½-inch Jiffy Mud and Resin mixer chucked to a ½-inch drill motor. Mix only full units. Thoroughly stir pigmented resin, then blend with cure and mix thoroughly until a uniform consistency for 3 minutes. Then pour mixture into an empty can. Mix again to uniformity. For large projects the use of a drum blender should be considered.

Application Data

Substrate clean concrete, free from laitance

Application methods pour and spread method

Potlife time (at 20°C/68°F) 45 minutes

Potlife time and drying times are dependent on temperature.

Environmental Conditions

The substrate and material temperature should be between 10 and 28°C (50 and 82°F). Maximum humidity of the prepared concrete substrate should be 4% measured over an average depth of 2 cm.

Recoat Times

Recoat times depend on temperature. Recoat times for Nu-Klad 807B at 20°C/68°F are:

Between scrape coats .. 12 hours (minium)

Between scrape coat

and self levelling coat ... 16 hours (minium)

72 hours (maximum)

Curing

Curing times depend on temperature. Nu-Klad 807B cures at 20°C/68°F as follows:

dry to walk on..... 2 days

dry to light traffic 4 days

dry for service 3 days

fully cured 7 days

Minimum temperature for satisfactory cure is 10°C/50°F.

Cleaner Thinner 90-58

Nu-Klad 807B

Application Procedure

Pretreatment:

On smooth, flat, sound substrates. On smooth flat, porous substrates: prime with Nu-Klad 813B thinned with maximum 5% thinner, Prepare the surface of rough substrates with a Nu-Klad 807B scrape coat by pour and scrape coat technique after priming.

Normally 400 to 700 gram Nu-Klad 807B per m² is applied for scrape coat, depending on surface condition and roughness. For rough concrete surfaces a second scrape coat might be required.

Application of the self levelling coat

Pour the Nu-Klad 807B in strokes on the floor and spread using a flat trowel. After 10 minutes roll the surface with a pinroller to remove air bubbles. Apply a minimum of 1.5 mm.

Nu-Klad 807B has a smooth, high gloss finish after application.

Shipping Data

Packaging

resin 21.62 kg in 20 l can
cure 3.38 kg in 5 l can

Shipping weight (unit) .. approx. 26.9 kg

Shelf life 1 year from shipment date
when stored indoors in
unopened, original
containers at 5 to 40°C (41
to 104°F)

Nu-Klad 807B

Caution

This product is combustible. Keep away from heat and open flame. Keep container closed. Use with adequate ventilation. Avoid prolonged and repeated contact with skin. If used in confined areas, observe the following precautions to prevent damage to health:

1. Circulate adequate fresh air continuously during application and curing.
2. Use fresh air masks.

Do not empty into drains. Take precautionary measures against static discharges. For specific information on hazardous ingredients, required ventilation, possible consequences of contact, exposure and safety measures see Safety Data Sheet.

Safety

Since improper use and handling can be hazardous to health and cause of fire or explosion, safety precautions included with Product Data/Application Instruction and Material Safety Data Sheet must be observed during all storage, handling, use and drying periods.

Warranty

PPG warrants its products to be free from defects in material and workmanship. PPG's sole obligations and Buyer's exclusive remedy in connection with the products shall be limited, at PPG's option, to either replacement of products not conforming this warranty or credit to Buyer's account in the invoiced amount of the non-conforming products. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life, or one year from the delivery date, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

PPG makes no other warranties concerning the product. No other warranties, whether express, implied or statutory, such as warranties of merchantability or fitness particular purpose, shall apply. In no event shall PPG be liable for consequential or incidental damages.

Any recommendations or suggestion relating to the use of the products made by PPG, whether in its technical literature, or response to specific enquiry, or otherwise, is based on data believed to be reliable; however, the products and information are intended for use by Buyer's having requisite skill and know-how in the industry, and therefore it is Buyer to satisfy itself of the suitability of the products for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. Variation in environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results.

Limitation of Liability

PPG's liability on any claim of any kind, including claims based upon PPG's negligence or strict liability, for any loss or damage arising out of, connected with, or resulting from the use of the products, shall in no case exceed the purchase price allocable to the products or part thereof which give rise to the claim. In no event shall PPG be liable for consequential or incidental damages.

Due to PPG's policy of continuous product improvement, the information contained in this Product Data/Application Instructions sheet is subject to change without notice. It is the Buyer's responsibility to check that this issue is current prior to using the product. For the most up-to-date Product Data/Application Instructions always refer to the PPG Protective & Marine Coatings website at www.ppgpmc.com

To avoid any confusion that may arise through translation into other languages, the English version of the Product Data/Application Instructions will be the governing literature and must be referred to in case of deviations with product literature in other languages.

Condition of Sale

All our transactions are subject to our Terms and Conditions of Sale.